

PRODUCTS

Rev. 03 / 2011

		Tensile Strength		Tensile Modulus		Strain (%)	Density		Yield Tex (g/1000m)
		Ksi	MPa	Msi	GPa		lbs/in ³	g/cm ³	
A-38	3K	552	3800	34.1	235	1.6	0.064	1.76	200
	6K								400
A-42	12K	610	4200	34.8	240	1.8	0.064	1.76	800
	24K								1600
A-49 (*)	12K	711	4900	34.1	240	2.0	0.065	1.80	800
	24K								1600
Test Method		ISO 10618		ISO 10618		ISO 10618	ISO 10119		ISO 1889

Standart sizing: Epoxy
 (*) Development stage



Future Products:

- Short (Chopped) Carbon Fiber
- Large Tow Carbon Fiber